

Application No. 10/500,366

Docket No.: 22106-00060-US1

Amendment dated

Reply to Office Action of September 13, 2005

**AMENDMENTS TO THE SPECIFICATION**

Please amend the specification as follows:

**Page 1, Third Paragraph**

Although these methods ~~allow to obtain~~ produce satisfactory results, they have drawbacks, among which mention must certainly be made of the annealing process to which the copper is subjected due to the application of heat caused by the braze welding process. This heating, which can reach temperatures on the order of 700 °C for a few tens of seconds, causes a reduction and degradation of the mechanical characteristics of the copper.